

Technical datasheet

Preventive AQ-5T

Preventive AQ-5T is a dry-film corrosion preventive offering long-term indoor protection, specifically designed for dip coating, but can also be used as a spray rust preventive.

Application

Preventive AQ-5T is an ultra-low VOC, water displacing, dry film corrosion preventative which is a multipurpose product with applications in many sectors of industry

It is suitable for the protection of steel.

Preventive AQ-5T coatings remain flexible over a wide range. Application can be by dip, or spray (air assisted or airless) but the low viscosity of the product makes it particularly suitable for dip coating.

Removal

Preventive AQ-5T can be removed with a hydrocarbon solvents or a suitable aqueous cleaner.

Protection

Indoors >24 months (typical)

Storage

Store in dry conditions away from other combustible materials, heat and direct sunlight. Protect from frost

Typical Data

Specific Gravity at 20 °C	1.0
Film Type	Dry Film
Drying Time at 20 °C	Approximately 20 minutes
Viscosity (40°C)	2 cSt
Pour point °C	0
Dry film thickness	ASTM-D 1748
0.1 microns	>80 days
Flash point (SFCC) °C	None
Dry Film Thickness (Dip)	0.2 microns
Covering Capacity (Dip)	50 sqm /per litre